

## PRODUCT DATA SHEET

# SikaGrind®-180 KE

Strength enhancing grinding aid for the production of cement

### DESCRIPTION

SikaGrind®-180 KE is a liquid cement grinding aid with performance enhancing properties designed to increase the output of cement grinding plants and obtain improved strength development for cements.

### USES

- Improve the production rate of the cement grinding system
- Increase the early strength of the cement

### CHARACTERISTICS / ADVANTAGES

SikaGrind®-180 KE is a dispersant with the following characteristics:

- Neutralisation of electrical charges on the surface of the cement particles
- Separation of the cement particles

SikaGrind®-180 KE provides the following advantages in the cement production:

- Enhanced grinding properties of the cement mill due to less accumulation of material on grinding balls and mill-liners
- Higher separator efficiency due to improved cement particle dispersion
- Reduced relative power consumption per ton of cement due to increased output of the grinding system (tons per hour)
- Easier achievement of the desired cement and improved powder flow characteristics.

SikaGrind®-180 KE gives the following advantages to the finished cement:

- Reduced quantity of “over-milled” particles in the cement granulometry and easier discharge of the silos
- Increased early strengths and economic cement design with clinker replacements

### PRODUCT INFORMATION

#### Composition

Aqueous blend of minerals and polymers

<b>Packaging</b>	<ul style="list-style-type: none"> <li>▪ 1 IBC</li> <li>▪ Tanker Deliver (when needed)</li> </ul>
<b>Appearance / Colour</b>	Light Brown Liquid/ Pale Yellow Liquid
<b>Shelf life</b>	12 months from date of production
<b>Storage conditions</b>	<p>Store in undamaged, unopened and sealed original containers at temperatures between +5 °C and +35 °C. Protect from frost, direct sunlight and contamination.</p> <p>Note: When delivered in bulk, the tanks and equipment used must be free from contaminants.</p>
<b>Density</b>	1.10 ± 0.02 kg/l (at +23 °C)
<b>pH-Value</b>	10.0±1.0

## APPLICATION INFORMATION

<b>Recommended dosage</b>	Typical dosage rates of SikaGrind®-180 KE is between 0.5–2.0 kg per tonne of cement (0.05–0.20 % of total weight = cement clinker + additions). Prior plant trials are necessary to determine optimum dosage because of variables such as clinker properties, cement type, and others
<b>Compatibility</b>	Cements treated with SikaGrind®-180 KE are compatible in concretes produced with all commercial admixtures including air entrainers, water reducers, retarders and superplasticizers. The performance of concrete admixtures is not adversely affected by the use of SikaGrind®-180 KE.

## BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

### DISPENSING

SikaGrind®-180 KE is added onto the clinker feed shortly before the mill entrance or directly into the grinding mill (first or second compartment). Suitable dosage pumps with adjustable flow rates shall be used for accurate dosing. Note: Periodically, the end of the additive tube/hose shall be checked to ensure that it is not blocked!

## LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Kenya Limited**  
 Josh Industrial Estate  
 P.O Box 38645 · 00623 Nairobi · Kenya  
 Mobile: +254 711 140234 / +254 786  
 140234  
 Web: ken.sika.com

SikaGrind-180KE-en-KE-(04-2025)-1-2.pdf

**Product Data Sheet**  
**SikaGrind®-180 KE**  
 April 2025, Version 01.02  
 021407011000000446