

PRODUCT DATA SHEET

Sika® Injection-101 RC

Polyurethane flexible injection resin for temporary waterstopping

DESCRIPTION

Sika® Injection-101 RC is a 2-part, polyurethane, low viscous, fast foaming, water-reactive injection resin. It cures to a dense flexible foam.

USES

Sika® Injection-101 RC may only be used by experienced professionals.

- Temporary waterstopping of high water intrusions in cracks, joints and cavities in concrete and masonry.
- Waterstopping in special applications such as bored or sheet pile walls, anchor heads and microtunneling.
- To achieve permanent watertight crack sealing inject with Sika® Injection-201 CE or Sika® Injection-203 after temporary waterstopping.

CHARACTERISTICS / ADVANTAGES

- Foaming reaction only takes place in direct contact with water
- Can be injected as a single component system
- Free foaming expansion up to 40 times
- Can be accelerated using Sika® Injection-AC10 in cold temperatures (< + 10 °C)

SUSTAINABILITY

- FEICA Environmental Product Declaration (EPD)

APPROVALS / CERTIFICATES

- Compilation of certified polyurethanes and injection processes for use on structures and components of federal traffic routes ZTV-ING, Part 3, Section 5 (RISS), Sika® Injection-101 RC, Bundesanstalt für Strassenwesen, 20.01.2016
- Large-surface sealants suitability according to KTW recommendations, Sika® Injection-101 RC, LADR Zentrallabor, July 2019

PRODUCT INFORMATION

Composition	Water reactive polyurethane resin	
Packaging	Part A (Resin)	10 or 20 kg
	Part B (Hardener)	12,5 or 25 kg
	Refer to current price list for packaging variations.	
Shelf life	24 months from date of production	
Storage conditions	The product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging.	
Colour	Part A (Resin)	Colourless
	Part B (Hardener)	Brown

Density	Part A (Resin)	~1,0 kg/l	(ISO 2811)
	Part B (Hardener)	~1,25 kg/l	
	Values at +20 °C		
Viscosity	Part A (Resin)	~140 mPa·s	(ISO 3219)
	Part B (Hardener)	~155 mPa·s	
	Values at +20 °C		

TECHNICAL INFORMATION

Expansion	Expansion start	~15 seconds after contact with water	(EN 1406)
	Expansion end	~67 seconds	
	Values at +20 °C		

APPLICATION INFORMATION

Mixing ratio

Part A : Part B = 1:1 by volume

Reaction times

(PM 10081-11)

0 % Sika® Injection-AC10*		
Material temperature	Expansion start	Expansion end
+5 °C	~19 sec	~89 sec
+10 °C	~17 sec	~88 sec
+20 °C	~16 sec	~70 sec

5 % Sika® Injection-AC10*		
Material temperature	Expansion start	Expansion end
+5 °C	~12 s	~57 s
+10 °C	~11 s	~49 s
+20 °C	~10 s	~39 s

10 % Sika® Injection-AC10*		
Material temperature	Expansion start	Expansion end
+5 °C	~9 s	~41 s
+10 °C	~8 s	~37 s
+20 °C	~7 s	~35 s

* Dosage of Sika® Injection-AC10 in % by weight of Sika® Injection-101 RC (Parts A+B)

The data above are laboratory parameters and may deviate depending on the situation and conditions on site.

The reaction speed (foam formation) is influenced by the temperatures of the mixed material, the structure and the contact water, plus the hydrodynamic conditions.

Smaller volumes can be used at a ratio of Part A : Part B = 1:1 by volume

Ambient air temperature	+5 °C min. / +35 °C max.	
Substrate temperature	+5 °C min. / +35 °C max.	
Pot Life	~2 hours (at + 20 °C)	(ISO 9514)

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

from the surface. Do not mix back into the liquids.

- Sika® Injection-101 RC is used for the temporary stopping of high water infiltration. Subsequently inject with Sika® Injection-201 CE or Sika® Injection-203 to achieve permanent watertight crack sealing.

IMPORTANT CONSIDERATIONS

- Remove any skin formation on the resin or hardener

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

Empty Parts A +B into a mixing vessel and mix slowly and thoroughly for at least 3 min (max. 250 rpm) until completely mixed.

After mixing, pour the material into the pump's feed container, stir briefly and use within the pot life.

If the substrate and/or ambient temperatures are < +10 °C, Sika® Injection-AC10 can be added to Sika® Injection-101 RC to accelerate the start of expansion.

APPLICATION METHOD / TOOLS

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Use injection pumps suitable for single part injection products.

CLEANING OF EQUIPMENT

Clean all tools and application equipment using the Sika® Injection Cleaning System

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kenya Limited

Mudher Industrial Complex, Mombasa
Road
P.O Box 38645 - 00623 Nairobi, Kenya
Mobile: +254 711 140234 / +254 786
140234
Web: ken.sika.com

Product Data Sheet

Sika® Injection-101 RC
July 2022, Version 02.02
020707010010000001

SikaInjection-101RC-en-KE-(07-2022)-2-2.pdf