

BUILDING TRUST

PRODUCT DATA SHEET Sika MonoTop[®]-1010 KE

Bonding primer and reinforcement corrosion protection cement based slurry containing recycled waste materials and corrosion inhibitors

DESCRIPTION

Sika MonoTop®-1010 KE is a 1-part, cementitious, polymer modified coating material used as bonding primer and reinforcement corrosion protection. It contains corrosion inhibitors as well as recycled waste materials which leads to a reduced carbon footprint compared to an equivalent performing mortar.

USES

Sika MonoTop®-1010 KE may only be used by experienced professionals in the following applications:

- Bonding primer as part of a concrete repair system
 Reinforcement corrosion protection as part of a con-
- crete repair system
- Interior and exterior use
- Suitable for control of anodic areas (Principle 11, method 11.1 of EN 1504-9)*

CHARACTERISTICS / ADVANTAGES

- Uses recycled waste materials
- Easy to use, just add water
- Good adhesion to concrete and steel
- Good resistance to water and chloride penetration
- Can be applied with a brush or by wet spray technique

SUSTAINABILITY

Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations

APPROVALS / CERTIFICATES

Confirms to EN 1504-7- Product for reinforcement corrosion protection

Composition Portland cement, cement replacement, re-dispersible polymer powder, selected aggregates and additive Packaging 25 kg bag Appearance / Colour Grey powder Shelf life 12 months from date of production Storage conditions Product must be stored in original, unopened and undamaged packaging in dry conditions at temperatures between +5 °C and +35 °C. Always refer to packaging Product declaration Pass (EN 1504-7) Soluble chloride ion content ≤ 0,01 % (EN 1015-17) **TECHNICAL INFORMATION**

Compressive strength

~40 MPa after 28 days

(EN 12190)

Product Data Sheet Sika MonoTop®-1010 KE May 2025, Version 01.01 020302020010000079

PRODUCT INFORMATION

Tensile strength in flexure	~6.0 MPa after 28 days	
Tensile adhesion strength	~1.8 MPa after 28 days	(EN 1542)
Diffusion resistance to water vapour	~100 μH ₂ O	
Corrosion test	Pass	(EN 15183)
Shear adhesion strength	Pass	(EN 15184)
Diffusion resistance to carbon dioxide	~1200 µCO,	

APPLICATION INFORMATION

Mixing ratio	For brush application	~5.75 L water (23 %) per 25 kg bag		
	For spraying application	~5.25 L water (21 %) per 25 kg bag		
Consumption	Bonding Primer	~1.5–2.0 kg of powder per m ² per 1 mm layer thickness depending on substrate roughness and thickness of layer applied.		
	Reinforcement Corrosion Protection	~2.0 kg of powder per m ² per 1 mm layer thickness		
	Consumption depends on the ro This figure is theoretical and do to surface porosity, surface pro	Consumption depends on the roughness and absorbency of the substrate. This figure is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
Yield	~14.3 L per 25 kg of powder			
Layer thickness	Bonding primer: sufficient to coat the concrete surface in a thin layer filling pores and voids. Reinforcement: corrosion protection - 2 mm minimum thickness.			
Ambient air temperature	+5 °C min. / +30 °C max			
Substrate temperature	+5 °C min. / +30 °C max			
Pot Life	 ~90 minutes for 20 % water (machine applied) ~120 minutes for 21 % water (manual application) 			
Waiting time to overcoating	 Apply concrete repair mortar wet on wet onto bonding primer. Apply concrete repair mortar wet on dry onto reinforcement corrosion protection. 			
Fresh mortar density	~2.0 Kg/L			
SYSTEMS				
System structure	Bonding Primer/ Reinforcement	Bonding Primer/ Reinforcement Corrosion Protection		
	Sika MonoTop [®] -1010	Reduced carbon footprint		
	Repair Mortar			
	Sika MonoTop [®] -4012	Reduced carbon footprint		
	Smoothing/ levelling mortar			
	SIKA MONOTOP*-3020	Reduced carbon footprint		

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

- Sika Method Statement: Concrete Repair Using Sika MonoTop[®] System • EN 1504-7 - Reinforcement corrosion protection

IMPORTANT CONSIDERATIONS

- Avoid application in direct sun and/or strong wind and/or rain.
- Do not add water over recommended dosage.

BUILDING TRUST



Product Data Sheet Sika MonoTop®-1010 KE May 2025, Version 01.01 020302020010000079

Apply only to stable, prepared substrates.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Concrete

- The concrete must be thoroughly clean, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials.
- De-laminated, weak, damaged and deteriorated concrete and where necessary sound concrete must be removed by suitable means.
- Ensure sufficient concrete is removed from around corroded reinforcement to allow cleaning for corrosion protection (where required) and compaction of the repair material.

Steel Reinforcement

- Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion must be removed.
- Surfaces must be prepared using abrasive blast cleaning techniques or high pressure water-blasting to Sa 2 (ISO 8501-1). Reference must be made to EN 1504-10 for specific requirements*

MIXING

- Mix with a low speed (<500 rpm) electric single or double paddle mixer or by hand for small quantities.
- Pour the recommended water quantity in a suitable mixing container.
- While stirring slowly, add the powder to the water and mix thoroughly for at least for 3 minutes

Sika Kenva Limited

Josh Industrial Estate P.O Box 38645 · 00623 Nairobi · Kenva Mobile: +254 711 140234 / +254 786 140234 Web: ken.sika.com

APPLICATION

Bonding primer

- Thoroughly pre-wet the prepared substrate a recommended 2 hours before application.
- Keep the surface wet and do not allow to dry.
- Before application remove excess water e.g. with a clean sponge.
- The surface must appear a dark matt appearance without glistering. Surface pores and voids must not contain water.
- Using a suitable clean brush, roller or suitable spraying equipment, cover the substrate in a thin layer filling all unevenness, pits and voids.

Reinforcement Corrosion Protection

- Using a suitable clean brush or spraying equipment, apply a first coat to cover the reinforcement bars ~1 mm thick
- When first coat is finger nail hard, apply a second layer ~1 mm thick. If using a spray method, protect substrate from excessive over-spray.
- Wait until completely dry before applying repair mortar.

CURING TREATMENT

Reinforcement corrosion protection: protect fresh coating immediately from premature drying and contamination using an appropriate curing method.

CLEANING OF EQUIPMENT

Clean all tools and equipment with water immediately after use. Hardened material can only be mechanically removed.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SikaMonoTop-1010KE-en-KE-(05-2025)-1-1.pdf

BUILDING TRUST

Product Data Sheet Sika MonoTop®-1010 KE May 2025. Version 01.01 020302020010000079