

PRODUCT DATA SHEET

SikaBit® Pro T-240 RT

4 mm anti-root plastomeric bituminous roof membrane, flexible at -15 °C

DESCRIPTION

SikaBit® Pro T-240 RT is an APP modified bituminous, torch applied, roof waterproofing membrane containing an anti-root additive. It is reinforced with a dimensionally stable non-woven polyester inlay. The underside has a polyethylene burn-off film for easy application. It can be applied to wood, metal and concrete substrates including over existing bitumen roofing membranes. Top surface finish: polyethylene film. Thickness: ~4,0 mm

USES

Roof waterproofing membrane for:

- Flat roofs under protective layers or ballast
- Roof gardens
- Sunken roof landscaping
- Gravel covered roofs
- Roof garden final waterproofing layer in contact with soil

CHARACTERISTICS / ADVANTAGES

- Resistant to humic acids and fertilisers
- Can be applied in contact with soil or where there is a risk of the membrane being damaged by roots
- Good watertightness
- High tensile strength
- High elongation and cold flexibility
- Good resistance to impact
- Easy to install by torching method
- Choice of primers to suit substrate and weather conditions

APPROVALS / CERTIFICATES

- CE marking and Declaration of Performance to EN 13707 - Reinforced bitumen sheets for roof waterproofing
- CE marking and Declaration of Performance to EN 13969 - Damp proofing for buildings, including basement tanking

PRODUCT INFORMATION

| | | |
|-----------------------------|---|-----------------------------------|
| Composition | APP modified bitumen with anti-root additive | |
| Reinforcing material | Non-woven spunbond polyester fabric stabilised with fibreglass | |
| Packaging | Roll size | |
| | Length | 8,00 m |
| | Width | 1,00 m |
| | Weight | ~32,8 kg (4,1 kg/m ²) |
| Shelf life | 36 months from date of production | |
| Storage conditions | Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging. | |

| | | |
|----------------------------|--------------|-------------------|
| Appearance / Colour | Top surface | Polyethylene film |
| | Backing | Polyethylene film |
| Length | 8 m -1 % | |
| Width | 1 m -1 % | |
| Effective thickness | 4,0 mm ± 5 % | (EN 1849-1) |

TECHNICAL INFORMATION

| | | | |
|---------------------------------------|---------------------|--------------------|----------------------|
| Resistance to impact | ≥ 1250 mm at +23 °C | | (EN 12691- Method A) |
| Tensile strength | Longitudinal | 650 N/50 mm ± 20 % | (EN 12311-1) |
| | Transversal | 400 N/50 mm ± 20 % | |
| Elongation | Longitudinal | 40 % ± 15 % | (EN 12311-1) |
| | Transversal | 40 % ± 15 % | |
| Tear strength | Longitudinal | 150 N/50 mm ± 20 % | (EN 12310-1) |
| | Transversal | 180 N/50 mm ± 20 % | |
| Joint shear resistance | Longitudinal | 550 N/50 mm ± 20 % | (EN 12317-1) |
| | Transversal | 300 N/50 mm ± 20 % | |
| Flexibility at low temperature | -15 °C | | (EN 1109) |
| Flow resistance | ≥ 120 °C | | (EN 1110) |
| Watertightness | 60 kPa | | (EN 1928-Method B) |
| External fire performance | F roof | | (EN 13501-5) |
| Reaction to fire | Class E | | (EN 13501-1) |

APPLICATION INFORMATION

| | |
|--------------------------------|--------------------------|
| Ambient air temperature | +5 °C min. / +50 °C max. |
| Relative air humidity | 80 % max |
| Substrate temperature | +5 °C min. / +50 °C max. |

BASIS OF PRODUCT DATA

All technical data stated in this Product Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- At low temperatures, take care unrolling to avoid damaging the membrane.
- Use suitable footwear to avoid puncturing the membrane.
- Do not apply to wet, damp or unclean surfaces.
- Do not over-torch the membrane otherwise the polyester reinforcement (which melts at 260 °C) will be damaged making the membrane un-useable.
- If membrane is insufficiently heated, this can cause reduced adhesion to the substrate, between layers or on the overlaps. If this occurs, un-bonded areas must be lifted and re-torched.
- If a seasonal symbol is printed on the roll's label, it is

advisable to use the membrane during the indicated season

ECOLOGY, HEALTH AND SAFETY

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The supporting structure must be of sufficient structural strength to apply all new and existing layers of the roof build-up. Complete roof system must be designed and secured against wind uplift loadings. The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

Use the appropriate preparation equipment to achieve the required substrate quality.

APPLICATION METHOD / TOOLS

Installation procedure

Strictly follow installation procedures as defined in method statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

Priming

Apply the appropriate primer from the SikaBit® P or Sika® Igoflex® P range, at the correct consumption to the prepared dry surface and allow to dry before next application stage. Refer to the individual Product Data Sheets.

Alignment

Unroll, align and re-roll correctly before torching.

Overlaps

Side: 100 mm. End: 150 mm.

Torching

Use a gas burner to heat the substrate and the backing film on the underside of membrane. When the backing film starts to melt, the membrane is ready to stick. Roll the membrane forward and press firmly against the substrate to bond. Ensure a bead of melted bitumen is visible along the full length of the overlap sides and ends when laying.

Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for torch-applied membranes.

Protection

The membrane must be protected from damage during any ongoing site activities.

MAINTENANCE

To maintain the function of the roof during its

lifespan, it is advisable to arrange periodically for inspection of the membrane and detailing. Check the functionality of the auxiliary works, flashings, drainage outlets, overflow pipes etc. including removing leaves, moss and other vegetation, which could cause ponding on the roof and overload the drainage system.

LOCAL RESTRICTIONS

Please note that as a result of specific local regulations the declared data for this product may vary from country to country. Please consult the local Product Data Sheet for the exact product data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Kenya Limited

Mudher Industrial Complex, Mombasa
Road
P.O Box 38645 - 00623 Nairobi, Kenya
Mobile: +254 711 140234 / +254 786
140234
Web: ken.sika.com

Product Data Sheet

SikaBit® Pro T-240 RT
July 2022, Version 03.02
020920011990000232

